

BENÉT INTERNAL TECHNICAL REPORT

BITR NO. 91-3

X-RAY FLUORESCENCE ON-STREAM ANALYSIS OF STANDARD REFERENCE SOLUTION CONCENTRATIONS OF CHROMIUM PLATING AND POLISHING SOLUTIONS

SAMUEL SOPOK

JUNE 1991



**US ARMY ARMAMENT RESEARCH, DEVELOPMENT
AND ENGINEERING CENTER**

**CLOSE COMBAT ARMAMENTS CENTER
BENÉT LABORATORIES
WATERVLIET, N.Y. 12189-4050**

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED

20040218 270

DISCLAIMER

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

The use of trade name(s) and/or manufacturer(s) does not constitute an official indorsement or approval.

DESTRUCTION NOTICE

For classified documents, follow the procedures in DoD 5200.22-M, Industrial Security Manual, Section II-19 or DoD 5200.1-R, Information Security Program Regulation, Chapter IX.

For unclassified, limited documents, destroy by any method that will prevent disclosure of contents or reconstruction of the document.

For unclassified, unlimited documents, destroy when the report is no longer needed. Do not return it to the originator.

X-Ray Fluorescence On-Stream Analysis of Standard Reference Solution Concentrations of Chromium Plating and Polishing Solutions

Samuel Sopok
Benét Laboratories
Watervliet, NY 12189-4050

Abstract

X-ray fluorescence is evaluated as a means to quantitatively analyze standard reference solution concentrations of chromium plating and polishing solutions for chromium, sulfur, phosphorus, and iron in a continuous, on-stream fashion. The identical experiment was conducted at two different manufacturers of this type of instrument and included calibration/standardization with standard reference chromium plating and polishing solutions, analysis with coded standard reference chromium plating and polishing solutions, calibration/standardization with standard reference chromium plating and polishing wastewater solutions, and analysis with coded standard reference chromium plating and polishing wastewater solutions. Resultant data and their corresponding precisions show promise for this application and may complement current off-stream laboratory methods now in use. More work will be conducted to further determine the value of this technique.

Keywords

Chemical analysis, chromium plating solutions, polishing solutions, x-ray fluorescence on-stream analysis.

TABLE OF CONTENTS

Introduction	1
Approach	1
Results and Discussion.....	2
References.....	12

LIST OF TABLES

Table 1. Chromium Plating Standard Solutions	4
Table 2. Polishing Standard Solutions.....	4
Table 3. CrO_3 in Chromium Plating Solutions.....	5
Table 4. H_2SO_4 in Chromium Plating Solutions.....	5
Table 5. Fe in Chromium Plating Solutions	5
Table 6. H_3PO_4 in Polishing Solutions.....	6
Table 7. H_2SO_4 in Polishing Solutions.....	6
Table 8. Fe in Polishing Solutions	6
Table 9. Chromium Plating Solutions	7
Table 10. CrO_3 in Chromium Plating Solutions	7
Table 11. H_2SO_4 in Chromium Plating Solutions	7
Table 12. Fe in Chromium Plating Solutions.....	8
Table 13. Polishing Solutions.....	8
Table 14. H_3PO_4 in Polishing Solutions	8
Table 15. H_2SO_4 in Polishing Solutions	9
Table 16. Fe in Polishing Solutions.....	9

Table 17. CrO_3 in Chromium Plating Solutions.....	9
Table 18. H_2SO_4 in Chromium Plating Solutions.....	10
Table 19. Fe in Chromium Plating Solutions.....	10
Table 20. H_3PO_4 in Polishing Solutions.....	10
Table 21. H_2SO_4 in Polishing Solutions.....	10
Table 22. Fe in Polishing Solutions	11
Table 23. Experimental Wastewater Detection Limits	11
Table 24. Experimental Wastewater Detection Limits	11

Introduction

Current analytical methods now in use to determine chromium plating and polishing solution analytes are appropriate only for a laboratory environment (1-6). On-stream monitoring for the analyte concentrations of chromium plating and polishing solutions may complement present analytical methods and provide valuable production data. Recent work using x-ray fluorescence on-stream analysis to determine analyte concentrations of chromium plating solutions (7-9) appears to address part of the goal of on-stream monitoring discussed above at least for chromium plating solutions. This report evaluates the use of x-ray fluorescence on-stream analysis of standard reference solution concentrations of chromium plating and polishing solutions in relation to the stated goals.

Approach

Strict analytical chemistry methods and procedures are followed throughout this experimental section. An excellent source of reference for these methods and procedures is by Fritz and Schenk (10).

Many analytical reagent grade standard reference and coded standard reference solutions are required. These solutions are prepared to completely cover the operating ranges of normal production type chromium plating and polishing analyte concentrations in these solutions. Tables 1 - 2 give these chromium plating and polishing solutions and their analyte concentrations. The six references by Sopok (1-6) provide extensive information for preparing and chemically analyzing these standard reference solutions for all analytes listed in Tables 1 - 2. These analytical chemistry methods (1-6) are used for quality control purposes for these standard reference solutions.

The general analytical system used is an on-stream x-ray fluorescence spectrometer (approximate cost: \$70,000) that provides continuous elemental (chromium, sulfur, phosphorus, and iron) analyses of these solutions. Identical experiments were conducted on this type of instrumentation by Asoma Instruments Corp. (Austin, Texas) and Tracor X-ray Corp. (Mountain View, Calif.). Each company publishes manuals that are an excellent source of reference for operating conditions, operation, and maintenance of these instruments (11-12). All solutions are analyzed in triplicate and no dilutions are required. These experiments were conducted in a blind fashion due to the use of coded standard reference solutions.

The experimental approach included calibration/standardization with standard reference chromium plating and polishing solutions, analysis with coded standard reference chromium

plating and polishing solutions, calibration/standardization with standard reference chromium plating and polishing wastewater solutions, and analysis with coded standard reference chromium plating and polishing wastewater solutions. Uncoded calibration/standardization solution data were used to determine analyte concentrations of coded solution data.

Results and Discussion

Experimental Asoma and Tracor calibration/standardization data are given in Tables 3 - 8 for standard reference chromium plating and polishing solutions.

Experimental Asoma and Tracor analysis data are given in Tables 9 - 16 for coded standard reference chromium plating and polishing solutions. All experimental analysis data given in Tables 9 - 16 are coded and comprised of randomly duplicated solutions. Data given in Tables 17 - 22 show that the duplicate solutions in Tables 9 - 16 are statistically the same except in one case. The method used to determine this statistical evaluation involves a variation of the standard Student t-test and is extensively discussed elsewhere for an experiment with identical characteristics (3).

Experimental Asoma and Tracor calibration/standardization and analysis data are given in Tables 23 - 24 for standard reference chromium plating and polishing wastewater solutions. These two tables show experimental wastewater detection limits for chromium, sulfur, phosphorus, and iron in these chromium plating and polishing solutions.

An advantage of this experiment is that the standard reference chromium plating and polishing solutions covered the entire operational concentration ranges for each analyte thus optimizing calibration, standardization, and analysis. Another experimental advantage is that the analyte concentrations of these solutions were well-known since they were carefully prepared from analytical reagent materials. Finally, these analyte solution concentrations were verified by presently-used laboratory chemical analysis methods (1-6) for quality assurance purposes.

A disadvantage of this experiment is that only the solution analytes sought in these standard reference solutions varied, while the unsought solution analytes remained constant with respect to concentration that may provide better than normal data and precision. Another experimental disadvantage is that these standard reference solutions were never used for plating or polishing and, as a result, this experiment ignores the possible analysis effects of non-analyte chemical or particulate contaminants resulting from these processes.

An observation of this experiment is that each company had limited experience with chromium plating and polishing solution analysis, although the final methods developed were similar.

This experiment provides elemental analysis of chromium and does not distinguish between trivalent and hexavalent chromium. A second on-stream instrument (Spectronic-20 uv-visible spectrophotometer, on-stream mode, estimated cost \$1,000, Bausch and Lomb) separately provides a direct trivalent chromium analysis without dilution using a very small pathlength cell. Then the hexavalent chromium solution concentration is calculated by the difference between the x-ray fluorescence and uv-visible analysis methods.

The x-ray fluorescence chemical analysis method is non-destructive, applicable to multiple process streams, and requires no dilutions for these chromium plating and polishing solutions. In addition, monthly calibration, standardization, and maintenance are required for proper instrument use.

A second experiment is planned to further evaluate on-stream x-ray fluorescence for chromium plating and polishing solutions. This experiment will be conducted using actual chromium plating and polishing solutions. Elemental concentration ranges and their intervals will be simultaneously randomized to the extent possible, although the elemental operating ranges will be covered. A primary concern of this experiment is the possible analysis effects of non-analyte chemical or particulate contaminants resulting from normal chromium plating and polishing solutions.

Resultant data and their corresponding precisions show promise for this application and may complement current off-stream laboratory methods now in use. More work will be conducted to further determine the value of this technique.

Table 1. Chromium Plating Standard Solutions

Uncoded Standards	CrO₃ Values (Actual)	H₂SO₄ Values (Actual)	Fe Values (Actual)
A → E	240 - 260	2.70	3.75
F → J	250	2.50 - 2.90	3.75
K → O	250	2.70	0 - 7.50

Coded Standards	CrO₃ Values (Actual)	H₂SO₄ Values (Actual)	Fe Values (Actual)
W	245	2.60	1.88
X	245	2.60	1.88
Y	255	2.80	5.63
Z	255	2.80	5.63

All units are in grams/liter, wastewater detection limits were determined for each element between 10 → 1000 ppm concentration.

Table 2. Polishing Standard Solutions

Uncoded Standards	H₃PO₄ Values (Actual)	H₂SO₄ Values (Actual)	Fe Values (Actual)
1 → 5	640 - 720	840	7.50
6 → 10	680	795 - 885	7.50
11 → 15	680	840	0 - 15.00

Coded Standards	H₃PO₄ Values (Actual)	H₂SO₄ Values (Actual)	Fe Values (Actual)
96	660	818	3.75
97	660	818	3.75
98	700	863	11.25
99	700	863	11.25

All units are in grams/liter, wastewater detection limits were determined for each element between 10 → 1000 ppm concentration.

Table 3. CrO₃ in Chromium Plating Solutions - Experimental Calibration/Standardization Data

CrO ₃ Values (Actual)	Exp. Mean (n=3)		Exp. s.d. (n=3)	
	Asoma	Tracor	Asoma	Tracor
240.0	239.3	241.0	0.6	4.4
245.0	244.7	244.6	0.6	3.5
250.0	249.7	246.3	0.6	0.6
255.0	254.7	255.3	0.6	3.5
260.0	259.0	260.3	0.0	2.9

All units are in grams/liter; all solutions contain 2.70 g/l H₂SO₄ and 3.75 g/l Fe.

Table 4. H₂SO₄ in Chromium Plating Solutions-Experimental Calibration/Standardization Data

H ₂ SO ₄ Values (Actual)	Exp. Mean (n=3)		Exp. s.d. (n=3)	
	Asoma	Tracor	Asoma	Tracor
2.50	2.45	2.46	0.07	0.19
2.60	2.58	2.55	0.11	0.20
2.70	2.70	2.59	0.11	0.11
2.80	2.76	2.88	0.11	0.07
2.90	2.95	2.86	0.08	0.14

All units are in grams/liter; all solutions contain 250 g/l CrO₃ and 3.75 g/l Fe; chloride is an interference.

Table 5. Fe in Chromium Plating Solutions - Experimental Calibration/Standardization Data

Fe Values (Actual)	Exp. Mean (n=3)		Exp. s.d. (n=3)	
	Asoma	Tracor	Asoma	Tracor
0.00	0.05	0.00	0.23	0.19
1.88	1.67	1.91	0.20	0.12
3.75	3.85	3.85	0.22	0.07
5.63	5.62	5.54	0.18	0.04
7.50	7.20	7.52	0.28	0.05

All units are in grams/liter; all solutions contain 250 g/l CrO₃ and 2.70 g/l H₂SO₄.

Table 6. H_3PO_4 in Polishing Solutions - Experimental Calibration/Standardization Data

H_3PO_4 Values (Actual)	Exp. Mean (n=3)		Exp. s.d. (n=3)	
	Asoma	Tracor	Asoma	Tracor
640.0	640.6	643.0	0.6	5.6
660.0	660.0	657.0	0.0	7.2
680.0	680.7	683.7	1.2	7.2
700.0	700.3	702.7	0.6	7.4
720.0	720.0	719.7	1.0	6.7

All units are in grams/liter; all solutions contain 840 g/l H_2SO_4 and 7.50 g/l Fe.

Table 7. H_2SO_4 in Polishing Solutions - Experimental Calibration/Standardization Data

H_2SO_4 Values (Actual)	Exp. Mean (n=3)		Exp. s.d. (n=3)	
	Asoma	Tracor	Asoma	Tracor
795.0	795.3	800.3	1.2	19.5
818.0	817.0	827.3	1.0	8.5
840.0	840.3	851.0	0.6	5.6
863.0	862.7	870.3	1.2	10.3
885.0	884.7	892.7	1.5	6.8

All units are in grams/liter; all solutions contain 680 g/l H_3PO_4 and 7.50 g/l Fe.

Table 8. Fe in Polishing Solutions - Experimental Calibration/Standardization Data

Fe Values (Actual)	Exp. Mean (n=3)		Exp. s.d. (n=3)	
	Asoma	Tracor	Asoma	Tracor
0.00	0.19	0.05	0.29	0.05
3.75	3.76	3.66	0.27	0.05
7.50	7.36	7.45	0.22	0.04
11.25	11.20	11.29	0.31	0.08
15.00	14.94	14.95	0.28	0.05

All units are in grams/liter; all solutions contain 680 g/l H_3PO_4 and 840 g/l H_2SO_4 .

Table 9. Chromium Plating Solutions - Experimental Analysis Data

Sample Pair (Actual)	CrO ₃ Value (Actual)	H ₂ SO ₄ Value (Actual)	Fe Value (Actual)
W & X	245	2.60	1.88
Y & Z	255	2.80	5.63

All units are in grams/liter; all elements in each solution pair passed t-test for both Asoma and Tracor.

Table 10. CrO₃ in Chromium Plating Solutions - Experimental Analysis Data

CrO ₃ Values (Actual)	Exp. Mean (n=3)		Exp. s.d. (n=3)	
	Asoma	Tracor	Asoma	Tracor
245.0	245.0	246.3	0.0	2.1
245.0	245.7	245.0	0.6	3.6
255.0	255.7	256.7	0.6	2.1
255.0	255.7	256.7	0.6	3.2

All units are in grams/liter; 1st and 2nd solutions contain 2.60 g/l H₂SO₄ and 1.88 g/l Fe; 3rd and 4th solutions contain 2.80 g/l H₂SO₄ and 5.63 g/l Fe.

Table 11. H₂SO₄ in Chromium Plating Solutions - Experimental Analysis Data

H ₂ SO ₄ Values (Actual)	Exp. Mean (n=3)		Exp. s.d. (n=3)	
	Asoma	Tracor	Asoma	Tracor
2.60	2.59	2.68	0.09	0.06
2.60	2.58	2.62	0.08	0.15
2.80	2.80	2.72	0.08	0.19
2.80	2.77	2.76	0.11	0.15

All units are in grams/liter; 1st and 2nd solutions contain 245 g/l CrO₃ and 1.88 g/l Fe; 3rd and 4th solutions contain 255 g/l CrO₃ and 5.63 g/l Fe.

Table 12. Fe in Chromium Plating Solutions - Experimental Analysis Data

Fe Values (Actual)	Exp. Mean (n=3)		Exp. s.d. (n=3)	
	Asoma	Tracor	Asoma	Tracor
1.88	1.88	1.84	0.19	0.08
1.88	1.95	1.78	0.30	0.02
5.63	5.58	5.54	0.26	0.06
5.63	5.56	5.63	0.31	0.11

All units are in grams/liter; 1st and 2nd solutions contain 245 g/l CrO_3 and 2.60 g/l H_2SO_4 ; 3rd and 4th solutions contain 255 g/l CrO_3 and 2.80 g/l H_2SO_4 .

Table 13. Polishing Solutions - Experimental Analysis Data

Sample Pair (Actual)	H_3PO_4 Value (Benét)	H_2SO_4 Value (Benét)	Fe Value (Benét)
96 & 97	660	818	3.75
98 & 99	700	863	11.25

All units are in grams/liter; all elements in each solution pair passed t-test for both Asoma and Tracor.

Table 14. H_3PO_4 in Polishing Solutions - Experimental Analysis Data

H_3PO_4 Values (Actual)	Exp. Mean (n=3)		Exp. s.d. (n=3)	
	Asoma	Tracor	Asoma	Tracor
660.0	658.7	658.0	0.6	7.9
660.0	660.7	661.3	0.6	7.0
700.0	700.3	698.7	0.6	5.5
700.0	700.0	702.3	1.7	3.2

All units are in grams/liter; 1st and 2nd solutions contain 818 g/l H_2SO_4 and 3.75 g/l Fe; 3rd and 4th solutions contain 863 g/l H_2SO_4 and 11.25 g/l Fe.

Table 15. H₂SO₄ in Polishing Solutions - Experimental Analysis Data

H ₂ SO ₄ Values (Actual)	Exp. Mean (n=3)		Exp. s.d. (n=3)	
	Asoma	Tracor	Asoma	Tracor
818.0	817.7	812.3	0.6	5.7
818.0	817.7	822.3	1.2	5.5
863.0	862.7	858.0	1.5	9.5
863.0	862.3	857.0	0.6	4.4

All units are in grams/liter; 1st and 2nd solutions contain 660 g/l H₃PO₄ and 3.75 g/l Fe; 3rd and 4th solutions contain 700 g/l H₃PO₄ and 11.25 g/l Fe.

Table 16. Fe in Polishing Solutions - Experimental Analysis Data

Fe Values (Actual)	Exp. Mean (n=3)		Exp. s.d. (n=3)	
	Asoma	Tracor	Asoma	Tracor
3.75	3.85	3.82	0.23	0.05
3.75	3.64	3.76	0.30	0.05
11.25	11.22	11.19	0.26	0.04
11.25	11.15	11.21	0.27	0.03

All units are in grams/liter; 1st and 2nd solutions contain 660 g/l H₃PO₄ and 818 g/l H₂SO₄; 3rd and 4th solutions contain 700 g/l H₃PO₄ and 863 g/l H₂SO₄.

Table 17. CrO₃ in Chromium Plating Solutions - Experimental Analysis Data

CrO ₃ Values (Actual)	Exp. t		Exp. Mean (n=6)		Exp. s.d. (n=6)	
	Asoma	Tracor	Asoma	Tracor	Asoma	Tracor
245/245	2.0	0.5	245.3	245.7	0.5	2.7
255/255	0.0	1.2	255.7	256.7	0.5	2.4

All units are in grams/liter except t; 1st and 2nd solutions contain 2.60 g/l H₂SO₄ and 1.88 g/l Fe; 3rd and 4th solutions contain 2.80 g/l H₂SO₄ and 5.63 g/l Fe.

Table 18. H₂SO₄ in Chromium Plating Solutions - Experimental Analysis Data

H ₂ SO ₄ Values	Exp. t		Exp. Mean (n=6)		Exp. s.d. (n=6)	
	Asoma	Tracor	Asoma	Tracor	Asoma	Tracor
2.60/2.60	0.2	0.7	2.58	2.65	0.08	0.11
2.80/2.80	0.0	0.3	2.79	2.74	0.08	0.16

All units are in grams/liter except t; 1st and 2nd solutions contain 245 g/l CrO₃ and 1.88 g/l Fe; 3rd and 4th solutions contain 255 g/l CrO₃ and 5.63 g/l Fe.

Table 19. Fe in Chromium Plating Solutions - Experimental Analysis Data

Fe Values (Actual)	Exp. t		Exp. Mean (n=6)		Exp. s.d. (n=6)	
	Asoma	Tracor	Asoma	Tracor	Asoma	Tracor
1.88/1.88	0.3	1.2	1.92	1.81	0.22	0.06
5.63/5.63	0.1	1.2	5.57	5.59	0.26	0.09

All units are in grams/liter except t; 1st and 2nd solutions contain 245 g/l CrO₃ and 2.60 g/l H₂SO₄; 3rd and 4th solutions contain 255 g/l CrO₃ and 2.80 g/l H₂SO₄.

Table 20. H₃PO₄ in Polishing Solutions - Experimental Analysis Data

H ₃ PO ₄ Values (Actual)	Exp. t		Exp. Mean (n=6)		Exp. s.d. (n=6)	
	Asoma	Tracor	Asoma	Tracor	Asoma	Tracor
660/660	4.1*	0.5	659.7	659.7	1.2	6.9
700/700	0.3	0.9	700.2	700.5	1.2	4.5

*Did not pass t-test but range of mean is only 2.0 g/l.

All units are in grams/liter except t; 1st and 2nd solutions contain 818 g/l H₂SO₄ and 3.75 g/l Fe; 3rd and 4th solutions contain 863 g/l H₂SO₄ and 11.25 g/l Fe.

Table 21. H₂SO₄ in Polishing Solutions - Experimental Analysis Data

H ₂ SO ₄ Values (Actual)	Exp. t		Exp. Mean (n=6)		Exp. s.d. (n=6)	
	Asoma	Tracor	Asoma	Tracor	Asoma	Tracor
818/818	0.0	2.2	817.7	817.3	0.8	7.5
863/863	0.4	0.2	862.5	857.5	1.0	6.6

All units are in grams/liter except t; 1st and 2nd solutions contain 660 g/l H₃PO₄ and 3.75 g/l Fe; 3rd and 4th solutions contain 700 g/l H₃PO₄ and 11.25 g/l Fe.

Table 22. Fe in Polishing Solutions - Experimental Analysis Data

Fe Values (Actual)	Exp. t		Exp. Mean (n=6)		Exp. s.d. (n=6)	
	Asoma	Tracor	Asoma	Tracor	Asoma	Tracor
3.75/3.75	1.0	1.5	3.75	3.79	0.26	0.06
11.25/11.25	0.3	0.8	11.18	11.20	0.24	0.03

All units are in grams/liter except t; 1st and 2nd solutions contain 660 g/l H₃PO₄ and 818 g/l H₂SO₄; 3rd and 4th solutions contain 700 g/l H₃PO₄ and 863 g/l H₂SO₄.

Table 23. Experimental Wastewater Detection Limits For Standard Chromium Plating Solutions

	Asoma	Tracor
Cr as CrO ₃	75	100
S as H ₂ SO ₄	100	500
Fe as Fe	100	50

All units are ppm.

Table 24. Experimental Wastewater Detection Limits For Standard Polishing Solutions

	Asoma	Tracor
P as H ₃ PO ₄	750	1000
S as H ₂ SO ₄	750	1000
Fe as Fe	500	100

All units are ppm.

References

- 1) S. Sopok, "Determination of Chromic Acid in Chromium Plating Solutions Using a Redox Titration and Indicator," U.S. Army RD&E Center Technical Report, Benét Laboratories, Watervliet, NY, (1989).
- 2) S. Sopok, "Determination of Sulfuric Acid in Chromium Plating Solutions Using Gravimetric Analysis," U.S. Army RD&E Center Technical Report, Benét Laboratories, Watervliet, NY, to be published.
- 3) S. Sopok, G. Friar, "Utilization of Ion Chromatography and Statistics to Determine Sulfuric Acid in Chromium Plating Solutions," U.S. Army RD&E Center Technical Report, Benét Laboratories, Watervliet, NY, to be published.
- 4) S. Sopok, "Determination of Cr(III) in Chromium Plating Solutions by UV-Visible Spectrophotometry," U.S. Army RD&E Center Technical Report, Benét Laboratories, Watervliet, NY, (1989).
- 5) S. Sopok, "Determination of Phosphoric and Sulfuric Acids in Polishing Solutions by Acid/Base Titration Using A pH Meter," U.S. Army RD&E Center Technical Report, Benét Laboratories, Watervliet, NY, (1989).
- 6) S. Sopok, "Determination of Iron in Chromium Plating and Polishing Solutions by Atomic Absorption Spectrometry," U.S. Army RD&E Center Technical Report, Benét Laboratories, Watervliet, NY, (1989).
- 7) Patent, Kawasaki Steel Corp. (Y. Hideko, A. Tadahiro, Y. Noriko, I. Takuji, H. Yoshiichi), "Method and Apparatus for the Determination of Chromium in Chromate Plating Solutions," Japanese Patents JP8714045A2 and JP6214045, (1987).
- 8) J. Cooper, "Rapid Analysis of Chromium Plating Solutions Using X-Ray Fluorescent Spectrometry," Trans. Inst. Met. Finish., 62, 151 (1985).
- 9) Y. Gohshi, O. Hirao, I. Suzuki, "Chemical State Analyses of Sulfur, Chromium and Tin by High Resolution X-Ray Spectrometry," Adv. X-Ray Anal., 18, 406 (1975).
- 10) J. Fritz, G. Schenk. Quantitative Analytical Chemistry, Allyn and Bacon, Boston 1987.
- 11) Asoma Model 8660 X-Ray Fluorescence On-Stream Analyzer Operation and Maintenance Manuals (Asoma Corp., Austin, TX), 1988.
- 12) Tracor Model 7000 X-Ray Fluorescence On-Stream Analyzer Operation and Maintenance Manuals (Tracor Corp., Mountain View, CA), 1988.

TECHNICAL REPORT INTERNAL DISTRIBUTION LIST

	NO. OF COPIES
CHIEF, DEVELOPMENT ENGINEERING DIVISION	
ATTN: SMCAR-CCB-D	1
-DA	1
-DC	1
-DI	1
-OP	1
-OR	1
-OS (SYSTEMS)	1
CHIEF, ENGINEERING SUPPORT DIVISION	
ATTN: SMCAR-CCB-S	1
-SE	1
CHIEF, RESEARCH DIVISION	
ATTN: SMCAR-CCB-R	2
-RA	1
-RE	1
-RM	1
-RP	1
-RT	1
TECHNICAL LIBRARY	5
ATTN: SMCAR-CCB-TL	
TECHNICAL PUBLICATIONS & EDITING SECTION	3
ATTN: SMCAR-CCB-TL	
OPERATIONS DIRECTORATE	1
ATTN: SMCWV-ODP-P	
DIRECTOR, PROCUREMENT DIRECTORATE	1
ATTN: SMCWV-PP	
DIRECTOR, PRODUCT ASSURANCE DIRECTORATE	1
ATTN: SMCWV-QA	

NOTE: PLEASE NOTIFY DIRECTOR, BENET LABORATORIES, ATTN: SMCAR-CCB-TL, OF ANY ADDRESS CHANGES.